The fixing adhesive

SPECIAL

OTTOCOLL[®] A 265 TopFix



Technical Datasheet

	1-component acrylic adhesive For indoor application			
Characteristic:	 High initital adhesion No fixation required Fast curing Short pressing and fixing times Compatible with natural stone Does not cause greasy deposits on natural stones Grindable and paintable after curing Solvent-free Store and transport frost-free 			
Fields of application:	 Bonding of stucco and ceiling profiles Bonding of gypsum plasterboards Bonding of cable ducts made of PVC Bonding of stone, natural stone and ceramic Bonding of insulating units, e. g. made of polystyrene, PVC, PU etc. Bonding of window sills, floor strips, decorative strips and stairs Bonding and mounting different materials, such as wood, wooden materials, plastics, metals and mineral substrates 			
Standards and tests:	 EMICODE® EC 1 Plus - very low emission Suitable for applications according to IVD instruction sheet no. 30+31+35 (IVD = German industry association sealants) French VOC-emission class A+ Classification according to building certification systems, see the sustainability data sheet Tested fire behaviour in accordance with EN 13501: class E 			
Important information:	 EMICODE® is a registered trademark of GEV e. V. (Düsseldorf, Germany) Before applying this product the user has to ensure that the materials in the area of contact (solid, liquid and gaseous) are compatible with it and also amongst each other and do not damage or alter (e. g. discolour) each other. As for the materials that will be used at a later stage in the surrounding area of the product the user has to clarify beforehand that the substances of content or evaporations do not lead to an impairment or alteration (e. g. discolouration) of the product. In case of doubt the user should consult the respective manufacturer of the material. Not suitable for the bonding of glass, polyethylene (PE), polypropylene (PP), polyamide (PA), polyfluoroethylene (PTFE), bituminous, waxy or oily substrates or similar. Not suitable for bonding of acrylic glass. Not suitable for non-corrosion protected metals and non-ferrous metals. May cause corrosion. Not suitable for bonds subject to moisture. 			

Technical Datasheet OTTOCOLL® TopFix Page 1 version: 42 / 33gb (31.01.2023, 8:58 h)





Technical properties:				
	Skin-forming time at 23 °C/50 % RH [m	inutes]	~ 10	
	Processing temperature from/to [°C]		+ 5 / + 35	
	Viscosity at 23 °C		pasty, stable	
	Density at 23 °C according to ISO 1183	-1 [g/cm³]	~ 1,3	
	Temperature resistance from/to [°C]		- 20 / + 80	
	Shelf life at 23 °C/50 % RH for cartridge	/foil bag [months]	24	
	These data are not suitable for the issue specifications.	e of specifications. P	lease contact OTTO-CHEMIE before issuing	
Pretreatment:	The adherent surfaces have to be clean, free from fat, dry and sustainable. All adherent surfaces must be clean and any contaminant such as release agents, preserving agents, grease, oil, dust, water, old adhesives or sealants and other substances which could affect adhesion, should be removed. Cleaning of non-porous substrates: Apply OTTO Cleaner T (airing time approx. 1 minute) using a clean, lint-free cotton cloth. Cleaning porous substrates: Clean surfaces with steel-wire brush e. g. or a grinding disk to remove loose particles.			
Application information:	At least one substrate must be absorbent. Apply OTTOCOLL® TopFix in dots or stripes. An all-over application (e. g. with a toothed spatula) is possible. Carry out bonding with OTTOCOLL® TopFix within the skin forming time (approx. 5 minutes). Fix or prop up heavy and highly stressed substrates. Remove adhesive residues with a moistened cloth immediately. Depending on the application, very absorbent substrates may require pre-treatment with a primer, e.g. OTTOFLEX® Deep primer. Due to the many possible influences during and after application, the customer always has to carry out trials first. Please observe the recommended shelf life which is printed on the packaging. We recommend to store our products in unopened original packagings dry (< 60 % RH) at temperatures of +15 °C up to +25 °C. If the products are stored and / or transported at higher temperatures / air humidity for longer periods (some weeks), a diminuition of durability or a change of material characteristics may arise.			
Deckezing		310 ml cartridge	e 20 l hobbock	
Packaging:	ovotor white	A265-04-C194		
	oyster-white Packaging unit	A205-04-0194	on request 1	
		1200	16	
	Pieces per pallet	1200	16	
Safety precautions:	Please observe the material safety data sheet. After curing the product is completely odourless.			
Disposal:	Information about disposal: Please refe	r to the material safe	ty data sheet.	
Disposal: Brand information:	Information about disposal: Please refe Styropor® is a registered brand of the c			

Technical Datasheet OTTOCOLL® TopFix Page 2 version: 42 / 33gb (31.01.2023, 8:58 h)

Hermann Otto GmbH · Krankenhausstr. 14 · 83413 Fridolfing, GERMANY Tel.:+49 8684-908-0 · Fax: +49 8684-1260 e-mail: info@otto-chemie.de · Internet: www.otto-chemie.com





infringement of third parties' rights and - if necessary - resolving it. For the rest our general terms and conditions apply, in particular regarding a possible liability for defects. You can find our general terms and conditions on our homepage: http://www.otto-chemie.de/en/terms-and-conditions

Technical Datasheet OTTOCOLL® TopFix Page 3 version: 42 / 33gb (31.01.2023, 8:58 h)

Hermann Otto GmbH · Krankenhausstr. 14 · 83413 Fridolfing, GERMANY Tel.:+49 8684-908-0 · Fax: +49 8684-1260 e-mail: info@otto-chemie.de · Internet: www.otto-chemie.com



